



LNE

Le progrès, une passion à partager
LABORATOIRE DE TRAPPES
29 avenue Roger Hennequin - 78197 Trappes Cedex
Tél. : 01 30 69 10 00 - Fax : 01 30 69 12 34

07 - - 1911

File G031707 - Document CEMATE/6 - Page 1/4

EUROPEAN REACTION TO FIRE CLASSIFICATION REPORT ACCORDING TO THE EUROPEAN STANDARD EN 13501-1

Notified Body by the French State besides the European Commission under number : 0071

Product standard : NF EN 14041
Resilient, textile and laminate floorcoverings

(free translation of French classification report n°G031707 CEMATE/5)

N°G031707 - CEMATE/6

Material submitted by : GERFLOR
50 Cours de la République
69627 VILLEURBANNE Cedex
FRANCE

Commercial trademark : TARALAY INITIAL CONFORT 33 et 43 / TRANSIT ACOUSTIC 33 et 43

Production site : GERFLOR Provence
Z.I du Bois des Lots
26130 SAINT PAUL TROIS CHATEAUX
FRANCE

Brief description : Floorcovering in PVC

Date of report : 2006, June 23rd

**Only full reproduction of the present document is authorized.
It contains 4 pages**

Laboratoire national de métrologie et d'essais

Établissement public à caractère industriel et commercial • Siège social : 1, rue Gaston Boissier - 75724 Paris Cedex 15 • Tél. : 01 40 43 37 00
Fax : 01 40 43 37 37 • E-mail : info@lne.fr • Internet : www.lne.fr • Siret : 313 320 244 00012 • NAF : 743 B • TVA : FR 92 313 320 244
Barclays Paris Centrale IBAN : FR76 3058 8600 0149 7267 4010 170 BIC : BARCFRPP

1. INTRODUCTION

This classification report defines the classification assigned to product in accordance with the procedures given in EN 13501-1.

2. DETAILS OF CLASSIFIED PRODUCT

2.1. NATURE AND END USE APPLICATION

VSM type (NF EN 651 standard) floorcovering.

2.2. DESCRIPTION

Characteristics product :

Product	Thickness in mm	Mass per unit square meter in g/m ²
<p>TARALAY INITIAL CONFORT 33 et 43 / TRANSIT ACOUSTIC 33 et 43</p>	<p>Wearing layer : 0.65 Pressed plasticized PVC</p> <p>Intercalary : 1.10 Coated PVC with reinforced glass woven</p> <p>Backing : 2.05 Chemical foam PVC</p> <p>Total thickness : 3.80 Tolerance : -0.15/+18</p>	<p>2975 Tolerance : -10/+13 %</p>

Text report to be followed on next page

3. TEST REPORTS AND TEST RESULTS IN SUPPORT OF THIS CLASSIFICATION

3.1. TEST REPORTS

Name of laboratory	Name of sponsor	Test report ref. n°	Test method
Laboratoire national de métrologie et d'essais 29 av. Roger Hennequin 78197 TRAPPES CEDEX	GERFLOR 50 Cours de la République 69627 VILLEURBANNE Cedex	File : G031707 CEMATE/4	Radiant panel EN ISO 9239-1

3.2. TEST RESULTS FOR FLOORINGS

Test method	Number of tests	Parameters	Results
EN ISO 9239-1 Glued to a particle board non-FR	4	Critical flux (kW/m ²) Smoke (%.min)	8.10 288

Text report to be followed on next page

4. CLASSIFICATION AND DIRECT FIELD APPLICATION

4.1. CLASSIFICATION

Fire behaviour	Smoke production	Flaming droplets
B_{fl}	s1	-

4.2. FIELD OF APPLICATION

This classification is valid for the product mentioned in § 2.2 or strictly and equally stipulated in the quoted production site.

Colour : various

Thickness : about 3.80 mm

Glued to wood substrate and A1 and A2 classified substrates

5. LIMITATIONS

5.1. RESTRICTIONS CONCERNING THE VALIDITY PERIOD OF THE CLASSIFICATION REPORT

None.

5.2. WARNING

This document does not represent type approval or certification of the product.

Trappes, the 23rd of June 2006

The Head of Fire Behaviour Division

Test Officer



Alain SAINRAT



Luc CHEVALIER