



<b>DESCRIPTION</b>			
Total thickness	EN 428	mm	2.00
	ASTM F386-02	inch	0.08
Wearlayer thickness	EN 429	mm	1.21
	ASTM F410-02	inch	0.048
Weight	EN 430	g/sq.m	2620
Width of sheet	EN 426	cm	200
	-	feet - inch	6'6"
Length of sheet	EN 426	lm	20
	-	feet - inch	66'
Coverage / roll	-	sq.ft	0
	-	sq.m	40
<b>CLASSIFICATION</b>			
Norm / Product specification	-	-	EN 649
	ASTM F1303-04	-	
European classification	EN 685	class	34 - 43
Fire rating	EN 13501-1	class	B <sub>fl</sub> -s1
	ASTM E648-08	class	Class I
	CAN/ULC S102.2	-	-
Static electrical propensity	EN 1815	kV	< 2
Slip resistance : Pendulum Test (dry & wet)	BS 7976-2	PTV	
Surface roughness R <sub>tm</sub>	-	µm	Rz ≥ 20
Slip resistance wet: ramp test with oil	DIN 51 130	class	R10
Slip resistance wet : bare foot	DIN 51 097	class	A
Slip resistance – ramp test	EN 13845 (annex C)	class	ESb
<b>PERFORMANCE</b>			
Wear resistance	EN 660.2	mm <sup>3</sup>	≤ 2
Wear group	EN 649	group	T
Type Binder content	ISO 10582	type	
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	≤ 0.10
Castor chair test (type W)	EN 425	-	P3
Thermal conductivity	EN 12524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Treatment	-	-	Sanosol®
Surface treatment	-	-	SparClean®
TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 100
<b>CE MARKING</b>			
	EN 14041	-	
		-	