

**DESCRIPTION**

Total thickness on grainside	EN 428	mm	2.20
	ASTM F386-02	inch	0.09
Weight	EN 430	g/sq.m	2200
Width of sheet	EN 426	cm	200
	-	feet - inch	6'6"
Length of sheet	EN 426	lm	20
	-	feet - inch	66'
Coverage / roll	-	sq.ft	430.56
	-	sq.m	40





**CLASSIFICATION**

Norm / Product specification	-	-	EN 649
	ASTM F1913-04	-	compliant
European classification	EN 685	class	34 - 43
Fire rating	EN 13501-1	class	C <sub>fl</sub> -s1
	ASTM E648-08	class	
	CAN/ULC S102.2	-	-
Slip resistance wet : bare foot	DIN 51 097	class	A B

**PERFORMANCE**

Wear resistance	EN 660.2	mm <sup>3</sup>	≤ 2.0
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	≤ 0.10
Thermal conductivity	EN 12524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 100

**CE MARKING**

	EN 14041	-	  
		-	