



DESCRIPTION			
Total thickness	EN ISO 24346 (EN 428)	mm	2.00
Wearlayer thickness	EN ISO 24340 (EN 429)	mm	0.70
Weight	EN ISO 23997 (EN 430)	g/sq.m	2560
Width of sheet	EN ISO 24341 (EN 426)	cm	200 / 400
Length of sheet	EN ISO 24341 (EN 426)	lm	20
CLASSIFICATION			
Norm / Product specification	-	-	EN ISO 10582 (EN 649)
European classification	EN ISO 10874 (EN 685)	class	34 - 43
Fire rating	EN 13 501-1	class	Bfl-s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance (1)	DIN 51130	class	R10
PERFORMANCES			
Wear resistance	EN 660.2	mm ³	≤ 2.0
Wear group	-	group	T
Type binder content	EN 10582	type	I
Dimensional stability	EN ISO 23999 (EN 434)	%	≤ 0.40
Residual indentation (requirement)	EN ISO 24343-1 (EN 433)	mm	≤ 0.10
Residual indentation (measure)	-	mm	≈ 0.05
Impact sound insulation	EN ISO 717-2	dB	≈ 6
Castor chair test (type W)	ISO 4918 (EN 425)	-	OK
Thermal conductivity	EN ISO 10456 (EN 12 524)	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Surface treatment	-	-	PUR+
Chemical products resistance (2)	EN ISO 26987 (EN 423)	-	OK
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/m ³	< 100
CE MARKING			
	EN 14041		

(1) For lifetime sustainable wet resistance, please refer to Tarasafe ranges.

(2) Regarding the resistance to chemicals, please download the corresponding leaflet from our website.